



LEGGERO 18 DRY

Knitwear

Data Sheet

Nm	NM 3/100
Ne	NE 60/3
Composition	100% COTTON AEGEAN GOTS COMPACT GASED LS
Gauge	16/18
Ply	1
Handfeel	Dry

Service & Availability

Stock Service	STOCK 4
Custom Colours	Si

Sustainability

Compliant ZDHC	Si
Compliant REACH	Si
Compliant GB	Si

Traceability

Fiber Origin	Turkey
Spinning Country	Turkey
Dyeing Country	Turkey
Custom Code	520543009000

Dyeing lots cones (KG)

Sampling	1/2/3/5/9/20/24/40/44
Production	90/120/130/165/220/250/330/380/660/702

Finishing

Carry out a gentle steaming to shape the garment before washing. Wash lightly in warm water to stabilize sizing and minimize shrinkage. Use a soft spin cycle and tumble dry at no more than 60–70°C. When pressing, use abundant steam. It's essential to run dedicated tests on your own knitted fabrics before beginning full-scale production, as results will vary based on your machinery, tension settings, and stitch type.

Stripes & Intarsio

Ask for a purpose specific dyeing when ordering yarn. For contrasting coloured sweaters, wash in water adding up to 10% of acetic acid, without using neither siliconic nor basic softeners.

Requirements

WASHING FASTNESS AT 40° C (WATER) – ISO 105/C06	Discharge on cotton: 4 Colour changing: 4
DRY CLEANING FASTNESS – ISO 105/D01	Discharge on cotton: 4 Colour changing: 4
FASTNESS TO ACID AND ALKALINE PERSPIRATION – ISO 105	Discharge on cotton: 4 Colour changing: 4
RUBBING FASTNESS – ISO 105/X12	Dry: 4 Wet - Light colors: 3/4 Wet - Medium dark colors: 3 Colour changing - Light colors: 4 Colour changing - Medium dark colors: 3/4