



Data Sheet

Nm	NM 3/50
Composition	85% AEGEAN COTTON GOTS LS 15 % CASHMERE
Gauge	12
Ply	1
Handfeel	Soft

Service & Availability

Stock Service	STOCK 12
Custom Colours	Si

Sustainability

Compliant ZDHC	Si
Compliant REACH	Si
Compliant GB	Si

Traceability

Custom Code	5206.46.00.90.00
-------------	------------------

Dyeing lots cones (KG)

Sampling	1/2/3/5/9/20/24/40/44
Production	90/120/130/165/220/250/330/380/660/702

Finishing

Carry out a gentle steaming to shape the garment before washing. Wash lightly in warm water to stabilize sizing and minimize shrinkage. Use a soft spin cycle and tumble dry at no more than 60–70°C. When pressing, use abundant steam. It's essential to run dedicated tests on your own knitted fabrics before beginning full-scale production, as results will vary based on your machinery, tension settings, and stitch type.

Stripes & Intarsio

Ask for a purpose specific dyeing when ordering yarn. For contrasting coloured sweaters, wash in water adding up to 10% of acetic acid, without using neither siliconic nor basic softeners.

TESSITURA

Requirements

WASHING FASTNESS AT 40° C (WATER) – ISO 105/C06	Discharge on cotton: 4 Colour changing: 4
DRY CLEANING FASTNESS – ISO 105/D01	Discharge on cotton: 4 Colour changing: 4
FASTNESS TO ACID AND ALKALINE PERSPIRATION – ISO 105	Discharge on cotton: 4 Colour changing: 4
RUBBING FASTNESS – ISO 105/X12	Dry: 4 Wet - Light colors: 4 Wet - Medium dark colors: 3 Colour changing - Light colors: 4 Colour changing - Medium dark colors: 4